

# Chen Tong Leather Lace Inspection

Property	Method	Unit	Standard		
			Full Grain Leather	Nubuck Leather	Suede Leather
Tensile Strength	TM94:2004	kg	Functional Square Shape: 25 (3.5mmx3mm) Round Shape: 15 (3.0mm Diameter)	Functional Square Shape: 25 (3.5mmx3mm)	Non-Functional
Crocking (Dry & Wet)	AATCC 8-2013	GSR	Dry :3 Wet:2	Dry :3 Wet:2	Dry :2.5 Wet:1.5
Colorfastness to Water	AATCC 107	BWS	2.5	1.5	1.5
Light Fastness	WTM 160	BWS	3	3	3
Lace to Lace Abrasion	WTM 154	Cycles	Functional Square Shape: 10,000 (3.5mmx3mm) Round Shape: 5,000 (3.0mm Diameter)	Functional Square Shape: 10,000 (3.5mmx3mm)	Non-Functional
Knot Slippage--Slippage	WTM 195	kg	1.2	1.2	Non-Functional
Knot Slippage--Pulling Undone	WTM 195	kg	3	3	Non-Functional

# 振通鞋帶檢測參考

項次	方法	單位	標準		
			面皮鞋帶	牛巴哥鞋帶	反毛皮鞋帶
拉力	TM94:2004	公斤	功能性 方條: 25 (3.5mmx3mm) 圓條: 15 (3.0mm 直徑)	功能性 方條: 25 (3.5mmx3mm)	非功能性
耐磨力(乾&濕)	AATCC 8-2013	級數	乾:3 濕:2	乾:3 濕:2	乾:2.5 濕:1.5
水中色牢度	AATCC 107	級數	2.5	1.5	1.5
耐黃變	WTM 160	級數	3	3	3
鞋帶與鞋帶間的磨損力	WTM 154	次數	功能性 方條: 10,000 (3.5mmx3mm) 圓條: 5,000 (3.0mm 直徑)	功能性 方條: 10,000 (3.5mmx3mm)	非功能性
防鬆脫	WTM 195	公斤	1.2	1.2	非功能性
Knot Slippage--Pulling Undone	WTM 195	公斤	3	3	非功能性